
Vacuum Casting Polyurethane: PT Flex 60 Liquid Rubber

Properties

Ultimate tensile strength	2.4 MPa
Tear strength	12250 N/m
Shore Hardness	60A
Elongation at break	235%

A flexible 60 Shore A fast-curing rubber. More rigid than PT Flex 50, but excellent for casting decorative objects, production parts, tools, models, patterns, duplicate masters and more.

Can be pigmented or dyed.

"Durable. Takes up detail."

Example applications



Gaiters



Overmoulding
and buttons



Mats



PARAGON
Rapid Technologies

What do you want to
make today?
