

---

## Vacuum Casting Polyurethane: PT Flex 85 Liquid Rubber

---

### Properties

Ultimate tensile strength	7.34 MPa
Tear strength	33200 N/m
Shore Hardness	85A
Elongation at break	250%

A firm 85 Shore A fast-curing rubber. Excellent for casting decorative objects, production parts, tools, models, patterns, duplicate masters and more.

Can be pigmented or dyed.

*"Rigid. Industrial. Practically tear proof."*

### Example applications



Oil seals



Rollers and casters



Detailed applications



**PARAGON**  
Rapid Technologies

What do you want to  
make today?

---